

Hexcel® HexWeb® CR-PAA™ 1/8-5056-0.002 Phosphoric Acid Anodized Aluminum Honeycomb

Category: Metal, Metal Foam, Mesh, or Honeycomb, Nonferrous Metal, Aluminum Alloy, 5000 Series Aluminum Alloy

Material Notes:

Grade is designated as "Cell Size-Alloy-Foil Gauge." The life cycle of aluminum honeycomb sandwich structures in a given application can be directly related to the quality of the bond between the face sheets that carry bending loads and the honeycomb that carries the shear loads. The adhesive is the interface between the facing and the core in the same way that the oxide on the aluminum and the primer that has been applied to it is the interface between the honeycomb substrate material and the bonding adhesive. This interface is critical to the performance of honeycomb bonded assemblies.HexWeb® CR-PAA™ is designed for aircraft structures that are exposed to demanding environmental conditions. HexWeb® CR-PAA™ outperforms standard MIL-C-7438 core in salt spray and HexWeb® crack propagation tests.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-CR-PAA-18-5056-0002-Phosphoric-Acid-Anodized-Aluminum-Honeycomb.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------|----------------------------|----------|
| Density | 0.130 g/cc | 0.00469 lb/in ³ | Nominal |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-------------|-------------|-------------------------------|
| Compressive Yield Strength | >= 8.27 MPa | >= 1200 psi | Bare, min |
| | >= 8.96 MPa | >= 1300 psi | Stabilized, min |
| | 12.1 MPa | 1750 psi | Bare, typ |
| | 13.1 MPa | 1900 psi | Stabilized, typ |
| Compressive Modulus | 3.00 GPa | 435 ksi | Stabilized, typ |
| Shear Modulus | 0.352 GPa | 51.0 ksi | Plate Shear, W Direction, typ |
| | 0.986 GPa | 143 ksi | Plate Shear, L Direction, typ |
| Shear Strength | >= 3.03 MPa | >= 440 psi | Plate Shear, W Direction, min |
| | 3.86 MPa | 560 psi | Plate Shear, W Direction, typ |
| | >= 5.10 MPa | >= 740 psi | Plate Shear, L Direction, min |
| | 6.52 MPa | 945 psi | Plate Shear, L Direction, typ |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China