Hexcel® HexWeb® CR-PAA[™] 3/8-5052-0.001 Phosphoric Acid Anodized Aluminum Honeycomb

Category : Metal , Metal Foam, Mesh, or Honeycomb , Nonferrous Metal , Aluminum Alloy , 5000 Series Aluminum Alloy

Material Notes:

Grade is designated as "Cell Size-Alloy-Foil Gauge." The life cycle of aluminum honeycomb sandwich structures in a given application can be directly related to the quality of the bond between the face sheets that carry bending loads and the honeycomb that carries the shear loads. The adhesive is the interface between the facing and the core in the same way that the oxide on the aluminum and the primer that has been applied to it is the interface between the honeycomb substrate material and the bonding adhesive. This interface is critical to the performance of honeycomb bonded assemblies.HexWeb® CR-PAA[™] is designed for aircraft structures that are exposed to demanding environmental conditions. HexWeb® CR-PAA[™] outperforms standard MIL-C-7438 core in salt spray and HexWeb® crack propagation tests.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-CR-PAA-38-5052-0001-Phosphoric-Acid-Anodized-Aluminum-Honeycomb.php

| Physical Properties | Metric | English | Comments |
|----------------------------|--------------|-----------------------------|-------------------------------|
| Density | 0.0256 g/cc | 0.000926 lb/in ³ | Nominal |
| | | | |
| Mechanical Properties | Metric | English | Comments |
| Compressive Yield Strength | >= 0.414 MPa | >= 60.0 psi | Bare, min |
| | >= 0.483 MPa | >= 70.0 psi | Stabilized, min |
| | 0.621 MPa | 90.0 psi | Bare, typ |
| | 0.655 MPa | 95.0 psi | Stabilized, typ |
| Compressive Modulus | 0.138 GPa | 20.0 ksi | Stabilized, typ |
| Shear Modulus | 0.0758 GPa | 11.0 ksi | Plate Shear, W Direction, typ |
| | 0.145 GPa | 21.0 ksi | Plate Shear, L Direction, typ |
| Shear Strength | >= 0.221 MPa | >= 32.0 psi | Plate Shear, W Direction, min |
| | 0.345 MPa | 50.0 psi | Plate Shear, W Direction, typ |
| | >= 0.414 MPa | >= 60.0 psi | Plate Shear, L Direction, min |
| | 0.586 MPa | 85.0 psi | Plate Shear, L Direction, typ |
| | | | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842



Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China