Hexcel® HexWeb® CR-PAA[™] 3/8-5052-0.003 Phosphoric Acid Anodized Aluminum Honeycomb

Category : Metal , Metal Foam, Mesh, or Honeycomb , Nonferrous Metal , Aluminum Alloy , 5000 Series Aluminum Alloy

Material Notes:

Grade is designated as "Cell Size-Alloy-Foil Gauge." The life cycle of aluminum honeycomb sandwich structures in a given application can be directly related to the quality of the bond between the face sheets that carry bending loads and the honeycomb that carries the shear loads. The adhesive is the interface between the facing and the core in the same way that the oxide on the aluminum and the primer that has been applied to it is the interface between the honeycomb substrate material and the bonding adhesive. This interface is critical to the performance of honeycomb bonded assemblies.HexWeb® CR-PAA[™] is designed for aircraft structures that are exposed to demanding environmental conditions. HexWeb® CR-PAA[™] outperforms standard MIL-C-7438 core in salt spray and HexWeb® crack propagation tests.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-CR-PAA-38-5052-0003-Phosphoric-Acid-Anodized-Aluminum-Honeycomb.php

Metric	English	Comments
0.0673 g/cc	0.00243 lb/in ³	Nominal
Metric	English	Comments
>= 2.31 MPa	>= 335 psi	Bare, min
>= 2.45 MPa	>= 355 psi	Stabilized, min
3.59 MPa	520 psi	Bare, typ
3.86 MPa	560 psi	Stabilized, typ
0.931 GPa	135 ksi	Stabilized, typ
0.200 GPa	29.0 ksi	Plate Shear, W Direction, typ
0.448 GPa	65.0 ksi	Plate Shear, L Direction, typ
>= 1.03 MPa	>= 150 psi	Plate Shear, W Direction, min
1.38 MPa	200 psi	Plate Shear, W Direction, typ
>= 1.76 MPa	>= 255 psi	Plate Shear, L Direction, min
2.14 MPa	310 psi	Plate Shear, L Direction, typ
	0.0673 g/cc Metric >= 2.31 MPa >= 2.45 MPa 3.59 MPa 3.86 MPa 0.931 GPa 0.200 GPa 0.200 GPa 0.448 GPa >= 1.03 MPa 1.38 MPa >= 1.76 MPa	0.0673 g/cc 0.00243 lb/in³ Metric English >= 2.31 MPa >= 335 psi >= 2.45 MPa >= 355 psi 3.59 MPa 520 psi 3.86 MPa 560 psi 0.931 GPa 135 ksi 0.200 GPa 29.0 ksi 0.448 GPa 65.0 ksi >= 1.03 MPa 200 psi 1.38 MPa 200 psi

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842



Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China