

## Hexcel® HexWeb® HDC-660 - 3/16 - 17.5 (R2) Heavy Density Core

Category : Other Engineering Material , Composite Core Material , Composite Fibers , Polymer , Thermoset , Carbon Fiber/Thermoset Composite

### Material Notes:

**Designation:** Material-Cell Size (inches)-DensityHexWeb® HDC is a fabric reinforced honeycomb, typically made from either fiberglass or carbon prepreg. A thermosetting node adhesive is used with either a thermoplastic or thermoset resin for the web impregnations. The product was developed for use in temperatures up to 500°F. Depending on the constituent resin system, the product may be suitable for short exposures at higher temperatures.**Features:** High compression strength non-metallic honeycomb available; Formability tailored to customer's needs; Low-moisture pickup; High thermal stability, very low coefficient of thermal expansion; Proven history in service; High corrosion resistance.**Applications:** HexWeb® HDC is used in sandwich structure as a replacement for potting compound in hard points or where extremely high compressive or shear strength is required. Using HexWeb® HDC in lieu of potting compound reduces process steps, improves part quality and reduces weight in the overall structure.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexWeb-HDC-660-316-175-R2-Heavy-Density-Core.php](http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HDC-660-316-175-R2-Heavy-Density-Core.php)

Physical Properties	Metric	English	Comments
Density	0.280 g/cc	0.0101 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	26.9 MPa	3900 psi	Stabilized
Shear Strength	7.58 MPa	1100 psi	Long Beam Shear, W Direction
	13.4 MPa	1950 psi	Long Beam Shear, L Direction

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China