

Hexcel® HexWeb® HRH-10/F50 - 5.0 Nonmetallic Flex-Core Honeycomb

Category : Other Engineering Material , Composite Fibers , Polymer , Thermoset , Aramid , Phenolic

Material Notes:

Designation: Material/Cell Size (cells per lineal foot in W direction)-DensityHexcel manufactures two types of nonmetallic reinforced plastic HexWeb® Flex-Core®: HexWeb® HRP - Fiberglasses cloth reinforced with a high temperature phenolic resin. This product provides good retention of strength for temperatures up to 350°F.HexWeb® HRH-10 - NOMEX® aramid paper reinforced with a high temperature phenolic resin. This product provides good retention of strength for temperatures up to 300°F.Features: Specifically designed for formability; Retains mechanical properties in the curved condition; Offers cost savings for curved panels.Applications: The HexWeb® Nonmetallic Flex-Core® cell configuration as opposed to the standard hexagonal cell honeycomb provides for exceptional formability into compound curvatures with reduced anticlastic curvature and controlled buckling of cell walls. When formed into tight radii, HexWeb® Nonmetallic Flex-Core® provides higher shear strengths than comparable hexagonal cores of equivalent density. HexWeb® Nonmetallic Flex-Core® applications exist wherever extreme curvature dictates a flexible cell geometry, e.g. radomes, ducts, leading edges of wings and stabilizers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-10F50-50-Nonmetallic-Flex-Core-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.0801 g/cc	0.00289 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 3.59 MPa	>= 520 psi	Bare, min
	>= 3.72 MPa	>= 540 psi	Stabilized, min
	4.62 MPa	670 psi	Bare, typ
	4.76 MPa	690 psi	Stabilized, typ
Shear Modulus	0.0359 GPa	5.20 ksi	Plate Shear, W Direction, typ
	0.0689 GPa	10.0 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 1.17 MPa	>= 170 psi	Plate Shear, W Direction, min
	1.48 MPa	215 psi	Plate Shear, W Direction, typ
	>= 2.07 MPa	>= 300 psi	Plate Shear, L Direction, min
	2.62 MPa	380 psi	Plate Shear, L Direction, typ

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China