

## Hexcel® HexWeb® HRH-36 - 1/8 - 3.5 Para-Aramid/Phenolic Core

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Aramid , Phenolic

### Material Notes:

Designation: Material-Cell Size (inches)-DensityHexWeb® HRH-36 is manufactured using KEVLAR® paper. The standard resin system is phenolic.Features: Mechanical properties equivalent to KOREX®; Low moisture pickup; Excellent thermal stability; Smooth cell wall finish.Applications: HexWeb® HRH-36 is a high performance non-metallic core, available in a wide range of densities, suitable for most composite sandwich applications. It can be readily heat formed to help produce complex components and offers similar mechanical properties to KOREX® core as well as comparable moisture pickup. In addition, HexWeb® HRH-36 offers a weight reduction over higher density NOMEX® honeycomb cores.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexWeb-HRH-36-18-35-Para-AramidPhenolic-Core.php](http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-36-18-35-Para-AramidPhenolic-Core.php)

Physical Properties	Metric	English	Comments
Density	0.0561 g/cc	0.00203 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	2.28 MPa	330 psi	Bare
	2.90 MPa	420 psi	Stabilized
Shear Modulus	0.0496 GPa	7.20 ksi	Plate Shear, W Direction
	0.110 GPa	15.9 ksi	Plate Shear, L Direction
Shear Strength	1.02 MPa	148 psi	Plate Shear, W Direction
	1.83 MPa	265 psi	Plate Shear, L Direction

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China