

Hexcel® HexWeb® HRH-78 - 1/4 - 3.0 Commercial Grade Nomex Honeycomb/Phenolic Resin

Category : Polymer , Thermoset , Phenolic

Material Notes:

Designation: Material-Cell Size (inches)-DensityHexWeb® HRH-78 is manufactured from commercial grade aramid paper sheets. A thermosetting adhesive is used to bond these sheets at the nodes, and after expanding, the block is dipped in a phenolic resin. After curing the resin, slices are cut to the desired thickness. Using this process, a wide range of cell sizes, paper thicknesses, and densities can be produced. An OX-Core® configuration featuring enhanced formability is available upon request.**Features:** High strength at low densities; Small cell sizes at low densities; Damage resistant under normal shop use; Formable; Flame resistant; Good bonding surfaces; Good thermal and electrical insulator.**Applications:** HexWeb® HRH-78 was developed by Hexcel to offer most of the characteristics of HexWeb® HRH-10 for exclusive use in non-aerospace applications, such as pleasure boats, skis, surfboards, ground antennas, and navy joiner panels.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-78-14-30-Commercial-Grade-Nomex-HoneycombPhenolic-Resin.php

Physical Properties	Metric	English	Comments
Density	0.0481 g/cc	0.00174 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	1.83 MPa	265 psi	Bare
	1.97 MPa	285 psi	Stabilized
Compressive Modulus	0.131 GPa	19.0 ksi	Stabilized, preliminary value obtained from limited testing
Shear Modulus	0.0207 GPa	3.00 ksi	Plate Shear, W Direction, preliminary value obtained from limited testing
	0.0317 GPa	4.60 ksi	Plate Shear, L Direction, preliminary value obtained from limited testing
Shear Strength	0.552 MPa	80.0 psi	Plate Shear, W Direction
	0.827 MPa	120 psi	Plate Shear, L Direction

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China