

Hexcel® HexWeb® HRP - 3/16 - 8.0 Fiberglass/Phenolic Honeycomb

Category : Ceramic , Glass , Glass Fiber , Other Engineering Material , Composite Core Material , Composite Fibers , Polymer , Thermoset , Phenolic

Material Notes:

Designation: Material-Cell Size (inches)-DensityHexWeb® HRP is a glass fabric reinforced honeycomb in which a heat-resistant phenolic resin is used both for initial and final impregnations. This product was developed for use at service temperatures up to 350°F. However, it is also well suited for short exposures at high temperatures. The HexWeb® HRP-series honeycomb is available in the standard hexagonal configuration, as well as in the two formale geometries - OX-Core® and Flex-Core®.**Features:** High strength up to 350°F; Good insulation and dielectric properties; Good bonding surface; Readily heat formed.**Applications:** HexWeb® HRP has proven to be an excellent core material for radomes, aircraft structural parts and fairings, heat shields, and other assemblies that see elevated temperature service.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRP-316-80-FiberglassPhenolic-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.128 g/cc	0.00463 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 7.58 MPa	>= 1100 psi	Bare, min
	>= 8.83 MPa	>= 1280 psi	Stabilized, min
	9.31 MPa	1350 psi	Bare, typ
	10.5 MPa	1530 psi	Stabilized, typ
Compressive Modulus	1.13 GPa	164 ksi	Stabilized, typ
Shear Modulus	0.131 GPa	19.0 ksi	Plate Shear, W Direction, typ
	0.228 GPa	33.0 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 2.55 MPa	>= 370 psi	Plate Shear, W Direction, min
	3.17 MPa	460 psi	Plate Shear, W Direction, typ
	>= 4.14 MPa	>= 600 psi	Plate Shear, L Direction, min
	5.17 MPa	750 psi	Plate Shear, L Direction, typ

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	350 °F	High strength retained

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China