

Hexcel® HexWeb® HRP - 3/8 - 8.0 Fiberglass/Phenolic Honeycomb

Category : Ceramic , Glass , Glass Fiber , Other Engineering Material , Composite Core Material , Composite Fibers , Polymer , Thermoset , Phenolic

Material Notes:

Designation: Material-Cell Size (inches)-DensityHexWeb® HRP is a glass fabric reinforced honeycomb in which a heat-resistant phenolic resin is used both for initial and final impregnations. This product was developed for use at service temperatures up to 350°F. However, it is also well suited for short exposures at high temperatures. The HexWeb® HRP-series honeycomb is available in the standard hexagonal configuration, as well as in the two formale geometries - OX-Core® and Flex-Core®.**Features:** High strength up to 350°F; Good insulation and dielectric properties; Good bonding surface; Readily heat formed.**Applications:** HexWeb® HRP has proven to be an excellent core material for radomes, aircraft structural parts and fairings, heat shields, and other assemblies that see elevated temperature service.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRP-38-80-FiberglassPhenolic-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.128 g/cc	0.00463 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 6.89 MPa	>= 1000 psi	Bare, min
	>= 8.14 MPa	>= 1180 psi	Stabilized, min
	9.65 MPa	1400 psi	Bare, typ
	10.6 MPa	1540 psi	Stabilized, typ
Compressive Modulus	1.03 GPa	150 ksi	Stabilized, typ
Shear Modulus	0.124 GPa	18.0 ksi	Plate Shear, W Direction, typ
	0.186 GPa	27.0 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 2.41 MPa	>= 350 psi	Plate Shear, W Direction, min
	3.10 MPa	450 psi	Plate Shear, W Direction, typ
	>= 3.72 MPa	>= 540 psi	Plate Shear, L Direction, min
	4.83 MPa	700 psi	Plate Shear, L Direction, typ

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	350 °F	High strength retained

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China