

## Hexcel® HexWeb® HRP/OX - 3/8 - 5.5 Fiberglass/Phenolic Honeycomb

Category : Ceramic , Glass , Glass Fiber , Other Engineering Material , Composite Core Material , Composite Fibers , Polymer , Thermoset , Phenolic

### Material Notes:

**Designation:** Material-Cell Size (inches)-DensityHexWeb® HRP is a glass fabric reinforced honeycomb in which a heat-resistant phenolic resin is used both for initial and final impregnations. This product was developed for use at service temperatures up to 350°F. However, it is also well suited for short exposures at high temperatures. The HexWeb® HRP-series honeycomb is available in the standard hexagonal configuration, as well as in the two formale geometries - OX-Core® and Flex-Core®.**Features:** High strength up to 350°F; Good insulation and dielectric properties; Good bonding surface; Readily heat formed.**Applications:** HexWeb® HRP has proven to be an excellent core material for radomes, aircraft structural parts and fairings, heat shields, and other assemblies that see elevated temperature service.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexWeb-HRPOX-38-55-FiberglassPhenolic-Honeycomb.php](http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRPOX-38-55-FiberglassPhenolic-Honeycomb.php)

Physical Properties	Metric	English	Comments
Density	0.0881 g/cc	0.00318 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 4.00 MPa	>= 580 psi	Bare, min
	>= 4.24 MPa	>= 615 psi	Stabilized, min
	4.83 MPa	700 psi	Bare, typ
	5.65 MPa	820 psi	Stabilized, typ
Compressive Modulus	0.414 GPa	60.0 ksi	Stabilized, typ
Shear Modulus	0.0689 GPa	10.0 ksi	Plate Shear, L Direction, typ
	0.117 GPa	17.0 ksi	Plate Shear, W Direction, typ
Shear Strength	>= 1.45 MPa	>= 210 psi	Plate Shear, L Direction, min
	1.86 MPa	270 psi	Plate Shear, L Direction, typ
	>= 1.90 MPa	>= 275 psi	Plate Shear, W Direction, min
	2.45 MPa	355 psi	Plate Shear, W Direction, typ

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	350 °F	High strength retained

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China