

Hexcel® Redux® 219/3-NA Foaming adhesive film

Category: Polymer, Adhesive, Film

Material Notes:

The Redux 200 series is a range fo foaming adhesive films presented in sheet form. They expand during the cure cycle to fill gaps and adhere strongly to all parts of the structure with which they come into contact. Redux foaming adhesive films are compative with Redux film adhesives. Features: High strength at temperatures from -67°F to 428°F; Less than 1% volatiles emitted during cure; Suitable for aluminum and fiber-reinforced composite sandwich constructions; Expansion ratios from 1:1.9 to 1:4.0. Application: Low exotherm for thicker sections. Associated Film Adhesives: Redux 319, 322, 330, 340 (SP), 641

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-Redux-2193-NA-Foaming-adhesive-film.php

| Mechanical Properties | Metric | English | Comments |
|-----------------------|----------------------|----------------------|---|
| Shear Strength | 6.00 MPa | 870 psi | Aluminum Double Lap Shear (0.06 inch gap) |
| | @Temperature 149 °C | @Temperature 300 °F | |
| | 10.0 MPa | 1450 psi | Aluminum Double Lap Shear (0.06 inch gap) |
| | @Temperature 22.2 °C | @Temperature 72.0 °F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|-----------------------|-----------------------|-----------------------|
| Cure Time | 60.0 min | 1.00 hour | Heat up rate 10°F/min |
| | @Temperature 177 °C | @Temperature 350 °F | |
| Shelf Life | 18.0 Month | 18.0 Month | |
| | @Temperature -17.8 °C | @Temperature 0.000 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China