

## Hexion Bakelite™ X30 Phenolic Formaldehyde Resin (discontinued \*\*)

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic

### Material Notes:

Phenolic molding compound, reinforced with cotton and sisal fibers, increased notched impact strength. Application areas: Covers for electrical and electromagnetic devices. Information provided by Bakelite AGBakelite AG became a part of Hexion in 2005.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexion-Bakelite-X30-Phenolic-Formaldehyde-Resin-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Hexion-Bakelite-X30-Phenolic-Formaldehyde-Resin-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	ISO 1183
Apparent Bulk Density	0.460 g/cc	0.0166 lb/in <sup>3</sup>	ISO 60
Linear Mold Shrinkage, Flow	0.0055 cm/cm	0.0055 in/in	Compression molding; ISO 2577

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	250 MPa	36300 psi	H 961/30; ISO 2039/P1
Tensile Strength at Break	50.0 MPa	7250 psi	5 mm/min; ISO 527 - 1/2
Tensile Modulus	7.50 GPa	1090 ksi	1 mm/min; ISO 527 - 1/2
Flexural Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	7.00 GPa	1020 ksi	ISO 178
Compressive Strength	220 MPa	31900 psi	Test specimen flat tested; ISO 604
Charpy Impact Unnotched	0.650 J/cm <sup>2</sup> @Temperature 23.0 °C	3.09 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179-1/2 eU
Charpy Impact, Notched	0.250 J/cm <sup>2</sup> @Temperature 23.0 °C	1.19 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179-1/2 eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 8.0 MPa	105 °C	221 °F	ISO 75-2
Shrinkage	0.450 % @Temperature 110 °C	0.450 % @Temperature 230 °F	Compression molding; ISO 2577

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	IEC 60093

Surface Resistance Electrical Properties	1.00e+10 ohm Metric	1.00e+10 ohm English	IEC 60093 Comments
Dielectric Constant	14 @Frequency 100 Hz	14 @Frequency 100 Hz	IEC 60250
Dielectric Strength	15.0 kV/mm @Thickness 1.00 mm	381 kV/in @Thickness 0.0394 in	IEC 60243-P1
Dissipation Factor	0.35 @Frequency 100 Hz	0.35 @Frequency 100 Hz	IEC 60250

Processing Properties	Metric	English	Comments
Feed Temperature	60.0 - 75.0 °C	140 - 167 °F	Injection molding
Nozzle Temperature	80.0 - 100 °C	176 - 212 °F	Injection molding
Melt Temperature	80.0 - 100 °C	176 - 212 °F	Injection molding
Mold Temperature	160 - 190 °C	320 - 374 °F	Injection molding
	160 - 190 °C	320 - 374 °F	Compression molding
Injection Pressure	>= 15.0 MPa	>= 2180 psi	Compression and injection cavity mold pressure
Back Pressure	0.500 - 2.00 MPa	72.5 - 290 psi	Injection molding
Cure Time	0.167 - 0.333 min	0.00278 - 0.00556 hour	Per 1 mm of wall thickness, injection molding
	0.333 - 0.667 min	0.00556 - 0.0111 hour	Per 1 mm of wall thickness, compression molding

Descriptive Properties	Value	Comments
Chromatic Spectrum	Subdued Colors	
Creep Rupture Strength	Good	
Holding Pressure	Approximately 40-60% of injection pressure	
Media Resistance	Good	
Moisture Absorption	100 mg	ISO 62, 24 hours at 23°C
Reserves by Peak Temperature	High	
Thermal Expansion	Slight	

Contact Songhan Plastic Technology Co.,Ltd.

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**