

Hippe PF WV 303 Wood veneer Reinforced Phenolic Resin - Sheet

Category : Polymer , Thermoset , Phenolic

Material Notes:

Parallel plied. Used in mechanical applications. Good mechanical properties. Information provided by Hippe.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hippe-PF-WV-303-Wood-veneer-Reinforced-Phenolic-Resin-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 - 1.40 g/cc	1.30 - 1.40 g/cc	IEC 1212-2 8.1

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 120 MPa	>= 17400 psi	IEC 1212-2 5.7
Flexural Strength	>= 180 MPa	>= 26100 psi	Perpendicular to laminations; IEC 1212-2 5.1
Flexural Modulus	>= 18.0 GPa	>= 2610 ksi	IEC 1212-2 5.2
Compressive Strength	>= 80.0 MPa	>= 11600 psi	Perpendicular to laminations; IEC 1212-2 5.3
Shear Strength	>= 15.0 MPa	>= 2180 psi	Parallel to laminations; IEC 1212-2 5.6
Charpy Impact Unnotched	>= 2.50 J/cm ²	>= 11.9 ft-lb/in ²	Parallel to laminations; IEC 1212-2 5.5.2

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	>= 100 V	>= 100 V	IEC 1212-2 6.4

Descriptive Properties	Value	Comments
Thermal Endurance	120 T.I.	IEC 1212-2 7.1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China