

Huntsman Araldite EPN 1180 Epoxy Phenol Novolac

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 175 to 182. Max color is 2. Comments/Applications: Epoxy functionality of 3.6. Much higher viscosity than EPN 1139 or EPN 1179. For higher heat and chemical resistance than PY 307-1 and EPN 1179. Used in matrix applications; filament winding, casting and pultrusion. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-EPN-1180-Epoxy-Phenol-Novolac.php

Physical Properties	Metric	English	Comments
Viscosity	20000 - 50000 cP	20000 - 50000 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China