

Huntsman Araldite LZ 8001 A-80 Brominated Resin

Category : Polymer , Thermoset , Epoxy

Material Notes:

Weight per Epoxide (EEW, g/eq) 410 to 460. Max color is 2. Comments/Applications: Bis A epoxy 80% solids in acetone (18-21% bromine). For use in manufacture of thin laminates, prepregs and rigid laminates for printed wiring boards requiring flame retardance. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-LZ-8001-A-80-Brominated-Resin.php

Physical Properties	Metric	English	Comments
Viscosity	1200 - 2500 cP	1200 - 2500 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China