

Huntsman HY 265 Cycloaliphatic Amine

Category : Polymer , Thermoset , Epoxy , Epoxy, Cycloaliphatic, Molded

Material Notes:

Approx. H+ equivalent weight 94. Mix Ratio with GY 6010 is 50. Comments/Applications: Modified cycloaliphatic polyamine adduct.

Excellent chemical resistance. Exceptional sulfuric acid (96-98%) resistance. High performance solvent free coatings for chemical storage tanks and chemical process equipment. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HY-265-Cycloaliphatic-Amine.php

Physical Properties	Metric	English	Comments
Viscosity	2700 - 10000 cP	2700 - 10000 cP	

Processing Properties	Metric	English	Comments
Pot Life	40 min	40 min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China