

Huntsman HY 355 Cycloaliphatic Amine

Category : Polymer , Thermoset , Epoxy , Epoxy, Cycloaliphatic, Molded

Material Notes:

Approx. H+ equivalent weight 48.5. Mix Ratio with GY 6010 is 26. Comments/Applications: Modified cycloaliphatic polyamine adduct for resistance to solvents and high temperature, especially when used with multifunctional epoxy resins such as EPN 1139 or PY 307-1. Tank linings, refineries, flooring, ship cargo tanks, secondary containment. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HY-355-Cycloaliphatic-Amine.php

Physical Properties	Metric	English	Comments
Viscosity	250 - 400 cP	250 - 400 cP	

Processing Properties	Metric	English	Comments
Pot Life	30 min	30 min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China