

Huntsman IROGRAN® A 85 P 4944 Ether-Based TPU-For Cable Industry

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

High temperature stability Information provided by Huntsman

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-IROGRAN-A-85-P-4944-Ether-Based-TPU-For-Cable-Industry.php

Physical Properties	Metric	English	Comments
Melt Flow	50 - 80 g/10 min	50 - 80 g/10 min	50-80 cm ³ /10 min; Melt Volume Rate

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	86	86	
Hardness, Shore D	35	35	
Tensile Strength at Break	40.0 MPa	5800 psi	
Elongation at Break	550 %	550 %	
Tear Strength	60.0 kN/m	342 pli	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China