

Huntsman IROGRAN® CA116-201 TPU-Polyester

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Introduction: IROGRAN CA116-201 is a high performance polyester based thermoplastic polyurethane intended for flat die extrusion applications. IROGRAN CA116-201 is part of the HUNTSMAN film and sheet product range and offers a specially designed, flexible plasticizer free product suitable for the preparation of extruded films. Performance Features: Low melt temperature High crystallization rate Good low temperature flexibility Good processability Applications: Adhesive film Lamination Information provided by Alliance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-IROGRAN-CA116-201-TPU-Polyester.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ASTM D792
Melt Index of Compound	15 g/10 min @Load 5.00 kg, Temperature 190 °C	15 g/10 min @Load 11.0 lb, Temperature 374 °F	MVR, [cm ³ /10 min]

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	95	95	Injection molded parts; ASTM D2240
Tensile Strength at Break	33.0 MPa	4790 psi	Injection molded parts; DIN 53504
Elongation at Break	400 %	400 %	Injection molded parts; DIN 53504
100% Modulus	0.00607 GPa	0.880 ksi	Injection molded parts; ASTM D412
300% Modulus	0.00658 GPa	0.954 ksi	Injection molded parts; ASTM D412
Tear Strength	92.9 kN/m	530 pli	Injection molded parts; ASTM D624

Thermal Properties	Metric	English	Comments
Melting Point	90.0 - 120 °C	194 - 248 °F	TMA Melt Range

Processing Properties	Metric	English	Comments
Feed Temperature	160 °C	320 °F	Extrusion
Middle Barrel Temperature	170 °C	338 °F	Extrusion
Adapter Temperature	170 °C	338 °F	Extrusion
Die Temperature	170 °C	338 °F	Extrusion

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China