

Huntsman PE1041 Film Extrusion Polyethylene (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

Homopolymer, and FDA compliant. Features: Good optical, medium impact strength, and good processability. Applications: Film extrusion: general purpose packaging. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170. Film properties based on 1.0 guage (25 µm) thickness; blow-up ratio 2:1. Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE1041-Film-Extrusion-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in ³	ASTM D1505
Thickness	25.4 microns	1.00 mil	
Melt Flow	2.0 g/10 min	2.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	52	52	ASTM D2240
Tensile Strength, Ultimate	11.0 MPa	1600 psi	ASTM D638
Tensile Strength, Yield	10.0 MPa	1450 psi	ASTM D638
Film Elongation at Break, MD	300 %	300 %	ASTM D882
Film Elongation at Break, TD	450 %	450 %	ASTM D882
Elongation at Break	550 %	550 %	ASTM D638
Modulus of Elasticity	0.248 GPa	36.0 ksi	Secant; ASTM D638
Secant Modulus, MD	0.173 GPa	25.1 ksi	ASTM D882
Secant Modulus, TD	0.207 GPa	30.0 ksi	ASTM D882
Dart Drop	3.15 g/micron	80.0 g/mil	ASTM D1709
Dart Drop Test	80.0 g	0.176 lb	ASTM D1709
Film Tensile Strength at Break, MD	20.0 MPa	2900 psi	ASTM D882
Film Tensile Strength at Break, TD	18.0 MPa	2610 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	96.0 °C	205 °F	ASTM D1525

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Haze	6.5 %	6.5 %	ASTM D1003
Gloss	65 %	65 %	at 45°; ASTM D523

Processing Properties	Metric	English	Comments
Melt Temperature	163 - 174 °C	325 - 345 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China