

Huntsman PE2072 Injection Molding Polyethylene (discontinued **)

Category: Polymer, Thermoplastic, Polyethylene (PE), LDPE, Low Density Polyethylene (LDPE), Molded

Material Notes:

Homopolymer and FDA compliant. Features: Very high flow rapid set-up characteristics, excellent clarity, gloss, and stiffness. Applications: Injection molding: lids and difficult to fill applications. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c) 2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170 Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE2072-Injection-Molding-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.924 g/cc	0.0334 lb/in³	ASTM D1505
Melt Flow	60 g/10 min	60 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	55	55	ASTM D2240
Tensile Strength, Ultimate	9.00 MPa	1310 psi	ASTM D638
Tensile Strength, Yield	12.0 MPa	1740 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Modulus of Elasticity	0.345 GPa	50.0 ksi	Secant; ASTM D638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	98.0 °C	208 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China