

IRPC Polimaxx Porene GA400 Acrylonitrile Butadiene Styrene

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Applications: injection molding electrical appliances electrical fans air conditioners floppy disks

Order this product through the following link:

http://www.lookpolymers.com/polymer_IRPC-Polimaxx-Porene-GA400-Acrylonitrile-Butadiene-Styrene.php

Physical Properties	Metric	English	Comments
Melt Flow	45 g/10 min @Load 10.0 kg, Temperature 220 Å°C	45 g/10 min @Load 22.0 lb, Temperature 428 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	112 @Thickness 6.35 mm, Temperature 23.0 Å°C	112 @Thickness 0.250 in, Temperature 73.4 Å°F	ASTM D785
Tensile Strength, Ultimate	41.2 MPa @Temperature 23.0 Å°C	5970 psi @Temperature 73.4 Å°F	ASTM D638
Flexural Yield Strength	60.8 MPa @Temperature 23.0 Å°C	8820 psi @Temperature 73.4 Å°F	ASTM D790
Flexural Modulus	2.21 GPa @Temperature 23.0 Å°C	320 ksi @Temperature 73.4 Å°F	ASTM D790
Izod Impact, Notched	1.67 J/cm @Thickness 6.35 mm, Temperature 23.0 Å°C	3.12 ft-lb/in @Thickness 0.250 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	94.0 Å°C @Thickness 6.35 mm	201 Å°F @Thickness 0.250 in	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	86.0 Å°C @Thickness 6.35 mm	187 Å°F @Thickness 0.250 in	ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Thermal Properties	^{HB} Metric	^{HB} English	Comments
	@Thickness 3.10 mm	@Thickness 0.122 in	

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 240 Å°C	356 - 464 Å°F	
Drying Temperature	80.0 - 90.0 Å°C @Time 7200 - 18000 sec	176 - 194 Å°F @Time 2.00 - 5.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China