

IRPC Polimaxx Porene KU900 Acrylonitrile Butadiene Styrene

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Applications: extrusion sheet refrigerator door liners and inner box liners picnic coolers snow boats luggage cases

Order this product through the following link:

http://www.lookpolymers.com/polymer_IRPC-Polimaxx-Porene-KU900-Acrylonitrile-Butadiene-Styrene.php

Physical Properties	Metric	English	Comments
Melt Flow	7.0 g/10 min	7.0 g/10 min	ASTM D1238
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
	@Thickness 6.35 mm, Temperature 23.0 °C	@Thickness 0.250 in, Temperature 73.4 °F	
Tensile Strength, Ultimate	43.1 MPa	6260 psi	ASTM D638
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Yield Strength	59.3 MPa	8610 psi	ASTM D790
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Modulus	2.01 GPa	292 ksi	ASTM D790
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched	2.94 J/cm	5.51 ft-lb/in	ASTM D256
	@Thickness 6.35 mm, Temperature 23.0 °C	@Thickness 0.250 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	92.0 °C	198 °F	ASTM D648
	@Thickness 6.35 mm	@Thickness 0.250 in	
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ASTM D648
	@Thickness 6.35 mm	@Thickness 0.250 in	
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Processing Temperature	180 - 240 °C	356 - 464 °F	
Drying Temperature	80.0 - 90.0 °C @Time 7200 - 18000 sec	176 - 194 °F @Time 2.00 - 5.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China