

Industeel SIRIUS 800 Heat Resistant Alloy

Category : Metal , Superalloy , Iron Base

Material Notes:

Description: The SIRIUS® 800, H and H+ grades are three variants of a high chromium and nickel austenitic alloy which combines good corrosion and creep resistance. SIRIUS® 800 is employed at temperature below 600°C(1112°F) while SIRIUS® 800H and SIRIUS® 800H+ are used above 600°C (1112°F). CLI heats obtained by vacuum degassing process have a tight control of the chemical analysis including residual elements in order to improve the weldability and in-service properties. Information provided by manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Industeel-SIRIUS-800-Heat-Resistant-Alloy.php

Physical Properties	Metric	English	Comments
Density	8.00 g/cc	0.289 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	>= 520 MPa	>= 75400 psi	Minimum Guaranteed
Tensile Strength, Yield	>= 210 MPa @Strain 0.200 %	>= 30500 psi @Strain 0.200 %	
Elongation at Break	>= 35 %	>= 35 %	
Modulus of Elasticity	196 GPa	28400 ksi	
Poissons Ratio	0.342	0.342	Calculated
Shear Modulus	73.0 GPa @Temperature 20.0 Â°C	10600 ksi @Temperature 68.0 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	13.5 Âµm/m-Â°C	7.50 Âµin/in-Â°F	
	@Temperature 0.000 - 100 Â°C	@Temperature 32.0 - 212 Â°F	
	14.5 Âµm/m-Â°C	8.06 Âµin/in-Â°F	
	@Temperature 0.000 - 100 Â°C	@Temperature 32.0 - 212 Â°F	
	15.5 Âµm/m-Â°C	8.61 Âµin/in-Â°F	
	@Temperature 0.000 - 400 Â°C	@Temperature 32.0 - 752 Â°F	
	17.0 Âµm/m-Â°C	9.44 Âµin/in-Â°F	

Thermal Properties	Metric @Temperature 0.000 - 000 Â°C	English @Temperature 32.0 - 119 Â°F	Comments
Specific Heat Capacity	0.502 J/g-Â°C @Temperature 20.0 Â°C	0.120 BTU/lb-Â°F @Temperature 68.0 Â°F	
Thermal Conductivity	13.0 W/m-K @Temperature 20.0 Â°C	90.2 BTU-in/hr-ftÂ²- Â°F @Temperature 68.0 Â°F	
Annealing Point	980 Â°C	1800 Â°F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	0.15 - 0.60 %	0.15 - 0.60 %	
Carbon, C	<= 0.10 %	<= 0.10 %	
Chromium, Cr	19 - 23 %	19 - 23 %	
Copper, Cu	<= 0.75 %	<= 0.75 %	
Iron, Fe	38.925 - 50.7 %	38.925 - 50.7 %	As remainder
Nickel, Ni	30 - 35 %	30 - 35 %	
Phosphorous, P	<= 0.020 %	<= 0.020 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Sulfur, S	<= 0.0050 %	<= 0.0050 %	
Titanium, Ti	0.15 - 0.60 %	0.15 - 0.60 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000100 ohm-cm @Temperature 20.0 Â°C	0.000100 ohm-cm @Temperature 68.0 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China