

## Industeel VIRGO 15.5PH 15Cr-5Ni-3Cu Precipitation Hardening Martensitic Stainless Steel (593°C - 4 hours - air cooling)

Category : Metal , Ferrous Metal , Martensitic , Stainless Steel , Precipitation Hardening Stainless , T S10000 Series Stainless Steel

### Material Notes:

Description: Alloy VIRGO 15.5 PH is a precipitation hardening martensitic stainless steel with 15% Cr, 5% Ni, 3.5% Cu and 0.3% Nb/Cb. The grade combines high mechanical properties and medium corrosion resistance. The VIRGO 15.5 PH grade is similar to the VIRGO 17.4 PH grade having equivalent mechanical properties. Due to the lower Chromium content and increased Nickel content the VIRGO 15.5 PH grade contains less ferrite which provides better through thickness properties particularly when considering thick plates. The corrosion behavior is close to 304 grade and better than 410 grade. The main applications are those of VIRGO 17.4 PH grade i.e. mechanical components and offshore industry when considering heavy plates. Information provided by manufacturer.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Industeel-VIRGO-155PH-15Cr-5Ni-3Cu-Precipitation-Hardening-Martensitic-Stainless-Steel-593C-4-hours-air-cooling.php](http://www.lookpolymers.com/polymer_Industeel-VIRGO-155PH-15Cr-5Ni-3Cu-Precipitation-Hardening-Martensitic-Stainless-Steel-593C-4-hours-air-cooling.php)

Physical Properties	Metric	English	Comments
Density	7.80 g/cc	0.282 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	>= 965 MPa	>= 140000 psi	Minimum Guaranteed
	1034 MPa	150000 psi	Typical
Tensile Strength, Yield	>= 790 MPa	>= 115000 psi	
	@Strain 0.200 %	@Strain 0.200 %	
Elongation at Break	931 MPa	135000 psi	Typical
	@Strain 0.200 %	@Strain 0.200 %	
Charpy Impact	>= 10 %	>= 10 %	
	17 %	17 %	Typical
	>= 20.0 J	>= 14.8 ft-lb	At RT, Transverse

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.070 %	<= 0.070 %	
Chromium, Cr	15 %	15 %	
Copper, Cu	3.5 %	3.5 %	
Iron, Fe	76.63 - 76.7 %	76.63 - 76.7 %	As remainder
Nickel, Ni	4.5 %	4.5 %	

Component Elements Properties	Metric	English	Comments
-------------------------------	--------	---------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China