

## Ineos ABS Centrex® 811 ASA Blend (discontinued \*\*)

Category : Polymer , Thermoplastic , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

### Material Notes:

Key Features: Unfilled High impact or high impact modified Light stabilized or stable to light U.V. stabilized or stable to weather Suitable processing methods: Injection molding Information provided by Bayer Polymers. LANXESS was spun-off from Bayer in early 2005. Business renamed Ineos ABS after INEOS acquires a majority shareholding under a JV with Lanxess in 2007. Subsequently Ineos acquired 100% of Ineos ABS.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ineos-ABS-Centrex-811-ASA-Blend-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_ineos-ABS-Centrex-811-ASA-Blend-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in <sup>3</sup>	
Melt Flow	9.0 g/10 min @Load 10.0 kg, Temperature 220 °C	9.0 g/10 min @Load 22.0 lb, Temperature 428 °F	cm <sup>3</sup> /10 min.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	37.9 MPa	5500 psi	
Elongation at Break	45 %	45 %	Nominal
Elongation at Yield	3.0 %	3.0 %	
Tensile Modulus	2.07 GPa	300 ksi	
Charpy Impact, Notched	4.59 J/cm <sup>2</sup>	21.8 ft-lb/in <sup>2</sup>	
	0.290 J/cm <sup>2</sup> @Temperature -30.0 °C	1.38 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	119 µm/m-°C @Temperature 20.0 °C	66.1 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	89.0 °C	192 °F	
Deflection Temperature at 1.8 MPa (264 psi)	77.0 °C	171 °F	
Vicat Softening Point	94.0 °C	201 °F	50°C/h 50N
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL Recognized

Thermal Properties	Metric	English	Comments
	@Thickness 3.00 mm	@Thickness 0.118 in	UL Recognized

Processing Properties	Metric	English	Comments
Melt Temperature	250 °C	482 °F	Injection Molding
Mold Temperature	60.0 °C	140 °F	Injection Molding
Injection Velocity	200 mm/sec	7.87 in/sec	
Injection Pressure	60.0 MPa	8700 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China