

Ineos ABS Lustran® H702

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Medium heat resistance, increased flow .,Property data per ISO test methods.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-H702.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Melt Flow	17 g/10 min @Load 10.0 kg, Temperature 220 °C	17 g/10 min @Load 22.0 lb, Temperature 428 °F	Estimated using room temperature density

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	46.0 MPa	6670 psi	
Elongation at Yield	2.6 %	2.6 %	
Tensile Modulus	2.50 GPa	363 ksi	
Charpy Impact Unnotched	10.0 J/cm ²	47.6 ft-lb/in ²	
	9.00 J/cm ² @Temperature -30.0 °C	42.8 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	1.60 J/cm ²	7.61 ft-lb/in ²	
	0.800 J/cm ² @Temperature -30.0 °C	3.81 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	0.800 Åµm/m-Å°C @Temperature 20.0 Å°C	0.444 Åµin/in-Å°F @Temperature 68.0 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	104 Å°C	219 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	99.0 Å°C	210 Å°F	
Vicat Softening Point	104 Å°C	219 Å°F	
	HB	HB	

Flammability UL 94			
Thermal Properties	Metric	English	Comments
	@ Thickness 1.60 mm	@ Thickness 0.0630 in	
Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.1	3.1	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.0050	0.0050	
Comparative Tracking Index	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0090	0.0090	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China