

Ineos ABS Lustran® H801

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

Material Notes:

High heat resistance, PC modified, low emission, increased flow.,Property data per ISO test methods.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-H801.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	
Melt Flow	10 g/10 min @Load 10.0 kg, Temperature 220 °C	10 g/10 min @Load 22.0 lb, Temperature 428 °F	Estimated using room temperature density

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	49.0 MPa	7110 psi	
Elongation at Yield	3.0 %	3.0 %	
Tensile Modulus	2.40 GPa	348 ksi	
Charpy Impact Unnotched	22.0 J/cm ²	105 ft-lb/in ²	
	16.0 J/cm ² @Temperature -30.0 °C	76.1 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	3.00 J/cm ²	14.3 ft-lb/in ²	
	1.20 J/cm ² @Temperature -30.0 °C	5.71 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	0.800 µm/m-°C @Temperature 20.0 °C	0.444 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	106 °C	223 °F	
Deflection Temperature at 1.8 MPa (264 psi)	99.0 °C	210 °F	
Vicat Softening Point	105 °C	221 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	$\geq 1.00 \times 10^{15}$ ohm	$\geq 1.00 \times 10^{15}$ ohm	
Dielectric Constant	3.0	3.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Constant	3.1	3.1	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	38.0 kV/mm	965 kV/in	
Dissipation Factor	0.0050	0.0050	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.0090	0.0090	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China