

Ineos ABS Lustran® QE 1455/L2, Injection Grade (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Injection molding grade, increased heat resistance, medium gloss, UV-stabilized grade. Applications: Automotive: body parts. Information provided by Bayer. LANXESS was spun-off from Bayer in early 2005. Business renamed Ineos ABS after INEOS acquires a majority shareholding under a JV with Lanxess in 2007. Subsequently Ineos acquired 100% of Ineos ABS.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-QE-1455L2-Injection-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	
Melt Flow	10 g/10 min	10 g/10 min	
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	49.0 MPa	7110 psi	
Elongation at Yield	2.0 %	2.0 %	
Tensile Modulus	2.60 GPa	377 ksi	
Charpy Impact Unnotched	0.700 J/cm ²	3.33 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.70 J/cm ²	8.09 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	94.0 °C	201 °F	
Vicat Softening Point	102 °C	216 °F	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	

Surface Resistance Electrical Properties	1.00e+15 ohm Metric	1.00e+15 ohm English	Comments
Dielectric Strength	29.0 kV/mm	737 kV/in	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China