

## Inno-Comp INNOPOLÂ® CS 2-3000 Polypropylene Block-Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

INNOPOLÂ® CS 2-3000 is a polypropylene block-copolymer compound. This grade is available in nature and custom colored form. INNOPOLÂ® CS 2-3000 is developed for producing injection molded automotive components. All information provided by INNO-COMP.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Inno-Comp-INNOPOL-CS-2-3000-Polypropylene-Block-Copolymer.php](http://www.lookpolymers.com/polymer_Inno-Comp-INNOPOL-CS-2-3000-Polypropylene-Block-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in <sup>3</sup>	ISO 1183
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Linear Mold Shrinkage, Flow	0.014 cm/cm	0.014 in/in	ISO 294
Linear Mold Shrinkage, Transverse	0.012 cm/cm	0.012 in/in	ISO 294
Melt Flow	12 g/10 min	12 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	
Ash	0.50 %	0.50 %	ISO 3451-1/A
	@Temperature 900 Â°C	@Temperature 1650 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	30.0 MPa	4350 psi	50 mm/min; ISO 527-1,-2
Elongation at Yield	6.5 %	6.5 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	1.40 GPa	203 ksi	1 mm/min; ISO 527-1,-2
Charpy Impact, Notched	0.450 J/cm <sup>2</sup>	2.14 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Melting Point	163 Â°C	325 Â°F	DSC; ISO 11357-1,-3
Deflection Temperature at 0.46 MPa	110 Â°C	230 Â°F	

(56 psi) Thermal Properties	Metric	English	ISO 75-1-2 Comments
Deflection Temperature at 1.8 MPa (264 psi)	56.0 Å°C	133 Å°F	ISO 75-1,-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	FMVSS 302

Descriptive Properties	Value	Comments
Automotive Materials	Pass	FMVSS 302
Color	Natural	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China