

Intercontinental Polymers 552 PBT Polymer Type - Elastomer, Polyester Resin

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Unreinforced, Molded

Material Notes:

Applications: Engineering Resin - Modified Information provided by Intercontinental Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Intercontinental-Polymers-552-PBT-Polymer-Type-Elastomer-Polyester-Resin.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------|--------------|----------|
| Relative Viscosity | 1.6 - 1.7 cP | 1.6 - 1.7 cP | LCL-PR21 |
| Melt Flow | 20 g/10 min | 20 g/10 min | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|--------|---------|----------|
| Hardness, Shore D | 72 | 72 | |

| Optical Properties | Metric | English | Comments |
|----------------------|----------|----------|---------------|
| Gardner Color Number | 9.0 - 13 | 9.0 - 13 | + b; LCL-PR01 |
| | 74 - 86 | 74 - 86 | Rd; LCL-PR01 |

| Processing Properties | Metric | English | Comments |
|-----------------------|---------|---------|----------|
| Melt Temperature | 224 Â°C | 435 Â°F | LCL-PR29 |

| Descriptive Properties | Value | Comments |
|------------------------|---------------|----------|
| Black Specks | Max. 10/200 g | LCL-PR05 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China