

Ipiranga Petrochem GM 8250 HDPE

Category: Polymer, Thermoplastic, Polyethylene (PE), HDPE, High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

IPQ produces High Density Polyethylene (HDPE) for use by different segments of the plastics molding industry in several processes, including blow molding, extrusion and injection molding. To produce HDPE, IPQ employs Hoechst/Hostalen technology through the following steps: the ethene supplied by COPESUL is processed by Ipiranga PetroquÃmica in reactors to produce powdered polyethylene. The polyethylene then receives additives and is homogenized with stabilizers and taken to extruding presses where it is granulated and is ready for marketing. An integrated and computerized system controls the production, from the initial processing stages to end-product testing for later commercialization. Applications: gallonsbig bottles and drumsbig bottles for chemical products

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ipiranga-Petrochem-GM-8250-HDPE.php

Physical Properties	Metric	English	Comments	
Density	0.953 - 0.957 g/cc	0.0344 - 0.0346 lb/in³	ASTM D792-98	
High Load Melt Index	6.0 - 10 g/10 min	6.0 - 10 g/10 min		
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	ASTM D1238-00	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.0 MPa	3920 psi	ASTM D638-02
Elongation at Yield	8.2 %	8.2 %	ASTM D638-02
Flexural Modulus	1.03 GPa	149 ksi	2% secant; ASTM D790-02
Izod Impact, Notched	3.45 J/cm	6.46 ft-lb/in	ASTM D256-03

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China