

Ipiranga Petrochem PRA 0852 Polypropylene

Category : Polymer , Film , Thermoplastic , Polypropylene (PP) , Polypropylene, Film Grade

Material Notes:

The production of polypropylene (PP) employs Spheripol technology from Montell / Italy. This technology has been acclaimed all over the world and is known as clean technology, because it does not produce catalyst residues (due to its high catalytic yield). Raw materials are supplied by COPESUL. Following pre-treatment, they are sent, with the catalytic system, into two loop reactors and one gas-phase reactor. This plant produces PP homopolymer, random copolymer, heterophase copolymer and terpolymer. The product leaves the reactors in the shape of spherical grains. The grains are sent to the extrusion site, where stabilizers are added to them. They are then turned into pellets by an extruding press. The pelletized material is first sent to mixing and storage silos. Later, this material is sent to the packaging area. Applications: technical film for automatic packaging of food and textile industry film for laminating

Order this product through the following link:

http://www.lookpolymers.com/polymer_ipiranga-Petrochem-PRA-0852-Polypropylene.php

Physical Properties	Metric	English	Comments
Melt Flow	7.0 - 10 g/10 min @Load 2.16 kg, Temperature 190 Â°C	7.0 - 10 g/10 min @Load 4.76 lb, Temperature 374 Â°F	ASTM D1238-00

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	102	102	ASTM D785-98
Tensile Strength, Yield	33.0 MPa	4790 psi	ASTM D638-02
Elongation at Yield	9.4 %	9.4 %	ASTM D638-02
Flexural Modulus	1.22 GPa	177 ksi	1% secant; ASTM D790-02
Izod Impact, Notched	0.450 J/cm	0.843 ft-lb/in	ASTM D256-03

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 Â°C	194 Â°F	ASTM D648-97
Vicat Softening Point	139 Â°C	282 Â°F	ASTM D1525-97

Optical Properties	Metric	English	Comments
Haze	77 % @Thickness 2.20 mm	77 % @Thickness 0.0866 in	ASTM D1003A-00

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China