

Johnson Matthey Matti-sil 40Sn Cadmium Free Brazing Alloy

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

Material Notes:

A general purpose alloy, often used for refrigeration work.Optimum Joint Gap 0.075 - 0.2 mm.AWS A5.8-92 BAg-28BS EN 1044 1999
AG105Equivalent to Engelhard Silvaloy A-40TEquivalent to Handy & Harman Braze 402Equivalent to J W Harris Safety-Silv 40TInformation provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Matti-sil-40Sn-Cadmium-Free-Brazing-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	650 - 710 Â°C	1200 - 1310 Â°F	
Solidus	650 Â°C	1200 Â°F	
Liquidus	710 Â°C	1310 Â°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	30 %	30 %	
Silver, Ag	40 %	40 %	
Tin, Sn	2.0 %	2.0 %	
Zinc, Zn	28 %	28 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China