

KKPC KOSYN KBR 710L Polybutadiene Rubber (Low cis BR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Polybutadiene Rubber (Low cis BR) Characteristics: Low cis BR is different in cis content according to the production process and the catalyst. KKPC's low cis LBR has 35% cis content. LBR has high elasticity and reactivity containing about 14% vinyl bond structure. It is used in the tires of motorcycle, footwear, common industrial products, and also utilized as base polymer of HIPS (high impact polystyrene) which is widely used in cabinet of home appliances, interior decoration, and toys. Since these products have high Mooney viscosity and low solution viscosity, it's easier to control rubber particle size and reduce power consumption during processing. Applications: Footwear, HIPS products, mechanical products Additional Notes: cis-1,4 Contents: 34.5% Volatile Matter: 0.5% Ash Content: 0.01% Toluene insoluble gel: 0.01% Gel Rank: A This product is so sensitive to sunlight and humidity that it can be tarnished and caused deterioration of quality if exposed. It is recommended to store it in cool and shady area lest it should be exposed to direct sunlight. Do not expose to incompatible materials or contaminants. Data provided by Korea Kumho Petrochemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_KKPC-KOSYN-KBR-710L-Polybutadiene-Rubber-Low-cis-BR.php

Physical Properties	Metric	English	Comments
Viscosity	90 cP	90 cP	Viscosity of Solution; 5% Styrene
Mooney Viscosity	32 @Temperature 100 Â°C	32 @Temperature 212 Â°F	ML1+4

Descriptive Properties	Value	Comments
Color	7	APHA

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China