

KKPC Kuhmo HI 425TV High Flow/High Heat Resistant HIPS

Category: Polymer, Thermoplastic, Polystyrene (PS), Polystyrene, Impact Modified

Material Notes:

Key features: High-impact, High heat resistance. Common Uses: TV cabinets, phonograph housings, humidifiers, typewriter bodies, sporting goods, office appliance housings. HIPS is a functional resin made by copolymerization of styrene monomer and PBR. It shows excellent balance between impact-resistance and heat-resistance. Data provided by Korea Kumho Petrochemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_KKPC-Kuhmo-HI-425TV-High-FlowHigh-Heat-Resistant-HIPS.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in³	ASTM D792
Water Absorption	0.050 %	0.050 %	24 hr immersion; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D955
Melt Flow	4.5 g/10 min	4.5 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	64	64	ASTM D785
Tensile Strength, Ultimate	29.4 MPa	4270 psi	ASTM D638
Elongation at Break	63 %	63 %	ASTM D638
Flexural Yield Strength	40.1 MPa	5810 psi	ASTM D790
Flexural Modulus	1.713 GPa	248.5 ksi	ASTM D790
Izod Impact, Notched	0.988 J/cm	1.85 ft-lb/in	ASTM D256
	@Thickness 3.20 mm	@Thickness 0.126 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	unannealed; ASTM D648
Vicat Softening Point	99.0 °C	210 °F	ASTM D1525
Flammability, UL94	НВ	НВ	
	@Thickness 2.20 mm	@Thickness 0.0866 in	
	НВ	НВ	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	НВ	НВ	



Thermal Properties	Metrickness 3.20 mm	English @ Allohness 0.126 in	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China