

## Kingfa MAC-501 Modified PC/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

### Material Notes:

Features:Excellent balance propertiesGood weather resistanceGood impact strengthGood processing propertiesSuit for electro-

platingApplications:Injection moldingAutomobile license plateWater tank coverComputer and accessoriesInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kingfa-MAC-501-Modified-PCABS-Alloy.php](http://www.lookpolymers.com/polymer_Kingfa-MAC-501-Modified-PCABS-Alloy.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc @Temperature 23.0 Â°C	1.13 g/cc @Temperature 73.4 Â°F	ASTM D792
Water Absorption	0.20 % @Temperature 23.0 Â°C, Time 86400 sec	0.20 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0060 cm/cm @Temperature 23.0 Â°C	0.0050 - 0.0060 in/in @Temperature 73.4 Â°F	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	55.0 MPa	7980 psi	50mm/min; ASTM D638
Elongation at Break	60 %	60 %	50mm/min; ASTM D638
Flexural Strength	74.0 MPa	10700 psi	2mm/min; ASTM D790
Flexural Modulus	2.20 GPa	319 ksi	2mm/min; ASTM D790
Izod Impact, Notched	5.50 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	10.3 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.20 mm, Temperature 23.0 Â°C	NB @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 Â°C	257 Â°F	ASTM D648

Thermal Properties	@Thickness 6.40 mm Metric	@Thickness 0.252 in English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	105 Å°C @Thickness 6.40 mm	221 Å°F @Thickness 0.252 in	ASTM D648
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	ASTM D257
Dielectric Strength	28.0 kV/mm	711 kV/in	1.6mm; ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	<= 260 Å°C	<= 500 Å°F	
Rear Barrel Temperature	220 - 235 Å°C	428 - 455 Å°F	Start Point: 230Å°C
Middle Barrel Temperature	220 - 240 Å°C	428 - 464 Å°F	Start Point: 235Å°C
Front Barrel Temperature	230 - 250 Å°C	446 - 482 Å°F	Start Point: 240Å°C
Melt Temperature	220 - 240 Å°C	428 - 464 Å°F	Start Point: 235Å°C
Mold Temperature	40.0 - 80.0 Å°C	104 - 176 Å°F	Start Point: 60Å°C
Drying Temperature	90.0 - 105 Å°C @Time 14400 - 21600 sec	194 - 221 Å°F @Time 4.00 - 6.00 hour	Pre-dry
Back Pressure	0.300 - 1.00 MPa	43.5 - 145 psi	

Descriptive Properties	Value	Comments
Injection Speed	60-90%	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China