

Kingfa MAC-601 PC/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Features:Excellent balance propertiesHigh impact strengthGood electro-plating propertiesGood processing

propertiesApplications:Injection moldingAutomobile instrument panelElectrical and electronic partsComputer and accessoriesHousehold appliance thin wall partsInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-MAC-601-PCABS-Alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc @Temperature 23.0 Â°C	1.14 g/cc @Temperature 73.4 Â°F	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm @Temperature 23.0 Â°C	0.0050 - 0.0070 in/in @Temperature 73.4 Â°F	ASTM D955
Melt Flow	15 g/10 min @Load 5.00 kg, Temperature 260 Â°C	15 g/10 min @Load 11.0 lb, Temperature 500 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 50.0 MPa	>= 7250 psi	50mm/min; ASTM D638
Elongation at Break	>= 60 %	>= 60 %	50mm/min; ASTM D638
Flexural Strength	82.0 MPa	11900 psi	2mm/min; ASTM D790
Flexural Modulus	2.20 GPa	319 ksi	2mm/min; ASTM D790
Izod Impact, Notched	5.50 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	10.3 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.20 mm, Temperature 23.0 Â°C	NB @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	124 Â°C @Thickness 6.40 mm	255 Â°F @Thickness 0.252 in	ASTM D648
Deflection Temperature at 1.8 MPa	106 Â°C	223 Â°F	

Thermal Properties	Metric	English	ASTM D648 Comments
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	ASTM D257
Dielectric Strength	30.0 kV/mm	762 kV/in	1.6mm; ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	<= 265 Â°C	<= 509 Â°F	
Rear Barrel Temperature	230 - 240 Â°C	446 - 464 Â°F	Start Point: 240Â°C
Middle Barrel Temperature	230 - 250 Â°C	446 - 482 Â°F	Start Point: 245Â°C
Front Barrel Temperature	240 - 260 Â°C	464 - 500 Â°F	Start Point: 250Â°C
Melt Temperature	220 - 250 Â°C	428 - 482 Â°F	Start Point: 245Â°C
Mold Temperature	60.0 - 80.0 Â°C	140 - 176 Â°F	Start Point: 70Â°C
Drying Temperature	100 - 110 Â°C	212 - 230 Â°F	Pre-dry
	@Time 14400 - 21600 sec	@Time 4.00 - 6.00 hour	
Back Pressure	0.300 - 1.00 MPa	43.5 - 145 psi	

Descriptive Properties	Value	Comments
Injection Speed	60-90%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China