

Kingfa PBT-RG301 Flame Retardant, 30% Glass Fiber Reinforced PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

Features:Flame retardantHigh mechanical strengthHigh heat resistanceGood electric propertiesNo bloomingApplications:Injection moldingHousehold appliance partsBobbinLighting partsRelayLinkerInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-PBT-RG301-Flame-Retardant-30-Glass-Fiber-Reinforced-PBT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.61 g/cc	1.61 g/cc	ASTM D792
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Water Absorption	0.070 %	0.070 %	ASTM D570
	@Temperature 23.0 Å°C, Time 86400 sec	@Temperature 73.4 Å°F, Time 24.0 hour	
Linear Mold Shrinkage	0.0030 - 0.0090 cm/cm	0.0030 - 0.0090 in/in	ASTM D955
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength at Break	120 MPa	17400 psi	10mm/min; ASTM D638
Elongation at Break	2.6 %	2.6 %	10mm/min; ASTM D638
Flexural Strength	190 MPa	27600 psi	2mm/min; ASTM D790
Flexural Modulus	9.00 GPa	1310 ksi	2mm/min; ASTM D790
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Å°C	@Thickness 0.126 in, Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	220 Å°C	428 Å°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	210 Å°C	410 Å°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Thermal Properties Flammability, UL 94	^{V-0} Metric	^{V-0} English	Comments
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	<= 265 Å°C	<= 509 Å°F	
Rear Barrel Temperature	220 - 240 Å°C	428 - 464 Å°F	Start Point: 235Å°C
Middle Barrel Temperature	235 - 255 Å°C	455 - 491 Å°F	Start Point: 245Å°C
Front Barrel Temperature	240 - 265 Å°C	464 - 509 Å°F	Start Point: 255Å°C
Melt Temperature	240 - 260 Å°C	464 - 500 Å°F	Start Point: 250Å°C
Mold Temperature	50.0 - 70.0 Å°C	122 - 158 Å°F	Start Point: 60Å°C
Drying Temperature	120 - 140 Å°C @Time 14400 - 21600 sec	248 - 284 Å°F @Time 4.00 - 6.00 hour	Pre-dry

Descriptive Properties	Value	Comments
Glass Fiber Content (%)	30	
Injection Speed	Moderate to High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China