

Kingfa PET-RG30 Flame Retardant, 30% Glass Fiber Reinforced PET

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Glass Fiber Filled, Flame Retardant

Material Notes:

Features: Flame retardant High strength Good heat resistance Outstanding electrical properties Applications: Injection molding Connectors Relay Bobbins Sockets E & E parts Information Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-PET-RG30-Flame-Retardant-30-Glass-Fiber-Reinforced-PET.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.65 g/cc	1.65 g/cc	ASTM D792
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Water Absorption	0.070 %	0.070 %	ASTM D570
	@Temperature 23.0 Å°C, Time 86400 sec	@Temperature 73.4 Å°F, Time 24.0 hour	
Linear Mold Shrinkage	0.0030 - 0.0090 cm/cm	0.0030 - 0.0090 in/in	ASTM D955
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength at Break	140 MPa	20300 psi	10mm/min; ASTM D638
Elongation at Break	2.3 %	2.3 %	10mm/min; ASTM D638
Flexural Strength	210 MPa	30500 psi	2mm/min; ASTM D790
Flexural Modulus	10.5 GPa	1520 ksi	2mm/min; ASTM D790
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Å°C	@Thickness 0.126 in, Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	240 Å°C	464 Å°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	225 Å°C	437 Å°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Thermal Properties Flammability, UL 94	^{V-0} Metric	^{V-0} English	Comments
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	<= 270 Â°C	<= 518 Â°F	
Rear Barrel Temperature	235 - 255 Â°C	455 - 491 Â°F	Start Point: 245Â°C
Middle Barrel Temperature	245 - 265 Â°C	473 - 509 Â°F	Start Point: 250Â°C
Front Barrel Temperature	255 - 275 Â°C	491 - 527 Â°F	Start Point: 260Â°C
Melt Temperature	255 - 275 Â°C	491 - 527 Â°F	Start Point: 260Â°C
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	Start Point: 100Â°C
Drying Temperature	120 - 140 Â°C @Time 10800 - 18000 sec	248 - 284 Â°F @Time 3.00 - 5.00 hour	Pre-dry

Descriptive Properties	Value	Comments
Glass Fiber Content (%)	30	
Injection Speed	Moderate to High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China