

Kolon DIAMATÂ® EH

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, Extruded

Material Notes:

Description: DIAMATÂ® is a specially formulated high impact grade PMMA resin from KOLON. The acrylic composition results in an excellent balance of impact resistance and high modulus at reasonable pricing. DIAMATÂ® utilizes acrylic toughener technology resulting in consistent appearance, even after years of UV exposure. DIAMATÂ® EH is a resin for extrusion molding with excellent impact strength.

Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-DIAMAT-EH.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Water Absorption	0.40 %	0.40 %	ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0080 cm/cm	0.0030 - 0.0080 in/in	ASTM D955
Melt Flow	1.5 g/10 min	1.5 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	45	45	ASTM D785
Tensile Strength, Ultimate	39.2 MPa	5690 psi	ASTM D638
Flexural Strength	63.4 MPa	9200 psi	ASTM D790
Flexural Modulus	1.77 GPa	256 ksi	ASTM D790
Izod Impact, Notched	0.588 J/cm	1.10 ft-lb/in	ASTM D256
Falling Dart Impact	20.6 J	15.2 ft-lb	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 Â°C	194 Â°F	Load not specified; ASTM D648
Vicat Softening Point	96.0 Â°C	205 Â°F	ASTM D1525
Glass Transition Temp, Tg	105 Â°C	221 Â°F	ASTM D3418

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ASTM D542
Haze	<= 3.0 %	<= 3.0 %	ASTM D1003

Transmission Visible Optical Properties	90 % Metric	90 % English	ASTM D1003 Comments
Processing Properties	Metric	English	Comments
Rear Barrel Temperature	150 - 180 Â°C	302 - 356 Â°F	Injection
Middle Barrel Temperature	180 - 230 Â°C	356 - 446 Â°F	Injection
Front Barrel Temperature	210 - 240 Â°C	410 - 464 Â°F	Injection
Nozzle Temperature	220 - 245 Â°C	428 - 473 Â°F	Injection
Zone 1	200 - 220 Â°C	392 - 428 Â°F	Extrusion
Zone 2	210 - 230 Â°C	410 - 446 Â°F	Extrusion
Zone 3	220 - 240 Â°C	428 - 464 Â°F	Extrusion
Zone 4	210 - 235 Â°C	410 - 455 Â°F	Vent; Extrusion
Zone 5	225 - 240 Â°C	437 - 464 Â°F	Extrusion
Adapter Temperature	230 - 240 Â°C	446 - 464 Â°F	Extrusion
Die Temperature	220 - 240 Â°C	428 - 464 Â°F	Extrusion
Melt Temperature	220 - 235 Â°C	428 - 455 Â°F	Recommended for Injection
Mold Temperature	40.0 - 80.0 Â°C	104 - 176 Â°F	
Roll Temperature	80.0 - 100 Â°C	176 - 212 Â°F	Extrusion
Drying Temperature	70.0 - 80.0 Â°C	158 - 176 Â°F	
Dry Time	3 - 5 hour	3 - 5 hour	
Injection Pressure	78.45 - 137.3 MPa	11380 - 19910 psi	
Screw Speed	40 - 80 rpm	40 - 80 rpm	Extrusion

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China