

Kolon KOLEFINÂ® KO133MT20 M/F Reinforced Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

KOLEFINÂ® has excellent mechanical properties and its cost is lower than other engineering plastics. KOLEFINÂ® is widely used in the automotive industry and business applications. Good mechanical properties and for high heat resistance, low mold shrinkage, good processability. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOLEFIN-KO133MT20-MF-Reinforced-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	DIN 53479; ASTM D792
Water Absorption	0.30 %	0.30 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.011 - 0.013 cm/cm	0.011 - 0.013 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	DIN 53505; ASTM D785
Tensile Strength, Ultimate	35.3 MPa	5120 psi	DIN 53455; ASTM D638
Elongation at Break	37 %	37 %	DIN 53455; ASTM D638
Flexural Yield Strength	53.9 MPa	7820 psi	DIN 53455; ASTM D790
Flexural Modulus	2.55 GPa	370 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.392 J/cm	0.735 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	170 Â°C	338 Â°F	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	145 Â°C	293 Â°F	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.1	3.1	ASTM D150/DIN 53483
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	28.0 kV/mm	711 kV/in	ASTM D149/DIN 53481
Arc Resistance	130 sec	130 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China