

Kolon KOPA[®] KN131 General Purpose Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

KOPA[®] is a thermoplastic resin with excellent mechanical, thermal and electrical properties and is widely used in automobile and industrial parts. Good mechanical properties, outstanding self-lubrication and abrasion resistance, excellent chemical resistance, wide usage temperature, good impact absorbing characteristics. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOPA-KN131-General-Purpose-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	DIN 53479; ASTM D792
Water Absorption	1.8 %	1.8 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.013 - 0.015 cm/cm	0.013 - 0.015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	DIN 53505; ASTM D785
Tensile Strength, Ultimate	80.4 MPa	11700 psi	DIN 53455; ASTM D638
Elongation at Break	120 %	120 %	DIN 53455; ASTM D638
Flexural Yield Strength	118 MPa	17100 psi	DIN 53455; ASTM D790
Flexural Modulus	2.65 GPa	384 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.686 J/cm	1.29 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	80.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	DIN 53752; ASTM D696
	@Temperature 20.0 $\text{Å}^\circ\text{C}$	@Temperature 68.0 $\text{Å}^\circ\text{F}$	
Melting Point	220 $\text{Å}^\circ\text{C}$	428 $\text{Å}^\circ\text{F}$	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	180 $\text{Å}^\circ\text{C}$	356 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.0 $\text{Å}^\circ\text{C}$	149 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	^{3.4} Metric	^{3.4} English	Comments <small>/DIN 53483</small>
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149/DIN 53481
Arc Resistance	120 sec	120 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China