

Kolon KOPA® KN135G33HI Multi Reinforced Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

KOPA® is a thermoplastic resin with excellent mechanical, thermal and electrical properties and is widely used in automobile and industrial parts. Good mechanical properties, outstanding self-lubrication and abrasion resistance, excellent chemical resistance, wide usage temperature, good impact absorbing characteristics. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOPA-KN135G33HI-Multi-Reinforced-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	DIN 53479; ASTM D792
Water Absorption	0.40 %	0.40 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	DIN 53505; ASTM D785
Tensile Strength, Ultimate	118 MPa	17100 psi	DIN 53455; ASTM D638
Elongation at Break	5.0 %	5.0 %	DIN 53455; ASTM D638
Flexural Yield Strength	169 MPa	24500 psi	DIN 53455; ASTM D790
Flexural Modulus	5.88 GPa	853 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	1.67 J/cm	3.12 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	40.0 µm/m-°C	22.2 µin/in-°F	DIN 53752; ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	220 °C	428 °F	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	190 °C	374 °F	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	175 °C	347 °F	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
	3.5	3.5	

Dielectric Constant Electrical Properties	Metric @ Frequency 1e+6 Hz	English @ Frequency 1e+6 Hz	ASTM D150/DIN 53483 Comments
Dielectric Strength	22.0 kV/mm	559 kV/in	ASTM D149/DIN 53481
Arc Resistance	135 sec	135 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China