

Kolon KOPA[®] KN333G30CRN G/F Reinforced Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Oil resistant Applications Surge tanks Information provided by API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOPA-KN333G30CRN-GF-Reinforced-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ASTM D792
Moisture Absorption at Equilibrium	0.40 %	0.40 %	60% RH; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength	186 MPa	27000 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Flexural Strength	275 MPa	39900 psi	ASTM D790
Flexural Modulus	8.532 GPa	1237 ksi	ASTM D790
Izod Impact, Notched	1.08 J/cm	2.02 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	20.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	11.1 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Melting Point	255 $\text{Å}^\circ\text{C}$	491 $\text{Å}^\circ\text{F}$	ASTM D1525
Deflection Temperature at 0.46 MPa (66 psi)	250 $\text{Å}^\circ\text{C}$	482 $\text{Å}^\circ\text{F}$	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	247 $\text{Å}^\circ\text{C}$	477 $\text{Å}^\circ\text{F}$	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.6	3.6	ASTM D150
Dielectric Strength	21.0 kV/mm	533 kV/in	ASTM D149
Arc Resistance	135 sec	135 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China