

## Kolon KOPET® KP133135 FR-PET Resin (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET)

### Material Notes:

KOPET® is the FR-PET which realizes the good properties and surface of injection molding with good mold process of short cooling time in low molding temperature. Good mold release, good surface of product, good harmonized mechanical properties with flame retardant. Information provided by US distributor, API-Kolon.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kolon-KOPET-KP133135-FR-PET-Resin-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Kolon-KOPET-KP133135-FR-PET-Resin-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in <sup>3</sup>	DIN 53479; ASTM D792
Water Absorption	0.050 %	0.050 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	DIN 53505; ASTM D785
Tensile Strength, Ultimate	98.1 MPa	14200 psi	DIN 53455; ASTM D638
Elongation at Break	3.0 %	3.0 %	DIN 53455; ASTM D638
Flexural Yield Strength	147 MPa	21300 psi	DIN 53455; ASTM D790
Flexural Modulus	8.83 GPa	1280 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.637 J/cm	1.19 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 µm/m-°C	16.7 µin/in-°F	DIN 53752; ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	254 °C	489 °F	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.5	3.5	ASTM D150/DIN 53483
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Dielectric Strength Electrical Properties	20.0 kV/mm Metric	508 kV/in English	ASTM D149/DIN 53481 Comments
Arc Resistance	120 sec	120 sec	ASTM D495

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China