

## Kolon Kopa® KN138R Nylon 6 Resin

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

### Material Notes:

KOPA is widely used in the automobile and industrial parts. General KOPA N-6 Features: Good mechanical properties, Extreme toughness, Outstanding self-lubrication and abrasion resistance, Excellent chemical resistance, Wide usage temperature, Good impact absorbing characteristics. Information provided by US distributor, API-Kolon.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kolon-Kopa-KN138R-Nylon-6-Resin.php](http://www.lookpolymers.com/polymer_Kolon-Kopa-KN138R-Nylon-6-Resin.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	DIN 53479; ASTM D792
Water Absorption	1.8 %	1.8 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.013 - 0.019 cm/cm	0.013 - 0.019 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	DIN 53505; ASTM D785
Tensile Strength, Ultimate	83.0 MPa	12000 psi	DIN 53455; ASTM D638
Elongation at Break	80 %	80 %	DIN 53455; ASTM D638
Flexural Yield Strength	108 MPa	15700 psi	DIN 53452; ASTM D790
Flexural Modulus	2.50 GPa	363 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.590 J/cm	1.11 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	80.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	DIN 53752; ASTM D696
	@Temperature 20.0 $\text{Å}^\circ\text{C}$	@Temperature 68.0 $\text{Å}^\circ\text{F}$	
Melting Point	220 $\text{Å}^\circ\text{C}$	428 $\text{Å}^\circ\text{F}$	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	180 $\text{Å}^\circ\text{C}$	356 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.0 $\text{Å}^\circ\text{C}$	149 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	<sup>3.4</sup> Metric	<sup>3.4</sup> English	Comments
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	/DIN 53483
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149/DIN 53481
Arc Resistance	120 sec	120 sec	ASTM D495

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China