

Kraton® D1101 (SBS) Linear Block Copolymer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

(SBS) styrene-butadiene-styrene block polymer. KRATON® Polymers require no premastication or vulcanization. They can be blended with thermoplastic polymers and significantly improve the impact qualities of the material, both at room and low temperature. This KRATON polymer meets FDA regulations as articles or as ingredients in articles intended for food contact. FDA clearances vary from one grade to another. For specific clearances, letters of certification will be provided on request. Applications: modified asphalts, thermoplastic and thermoset polymer modification, adhesives, sealants, coatings, sporting goods, film, and general elastomer compounding. Information provided by the manufacturer, Kraton® Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kraton-D1101-SBS-Linear-Block-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.940 g/cc	0.940 g/cc	
Brookfield Viscosity	4000 cP @Temperature 25.0 °C	4000 cP @Temperature 77.0 °F	Toluene solution. Neat polymer concentration, 25%w.
Melt Flow	<= 1.0 g/10 min	<= 1.0 g/10 min	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	69	69	10 seconds. Typical values on polymer compression molded at 150°C (300°F).
Tensile Strength, Ultimate	31.72 MPa	4601 psi	Tensile tester jaw separation 10 in/min (25.4 cm/min). Typical properties based on film cast from toluene solution.; ASTM D412
Elongation at Break	880 %	880 %	Tensile tester jaw separation 10 in/min (25.4 cm/min); ASTM D412
300% Modulus	0.00276 GPa	0.400 ksi	

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-80.0 °C	-112 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 - 1.00e+16 ohm-cm	1.00e+14 - 1.00e+16 ohm-cm	
Dielectric Strength	11.81 - 39.37 kV/mm	300.0 - 1000 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	150 - 200 Â°C	302 - 392 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China