

Kraton® D1102 + LDPE blend (10/90)

Category : Polymer , Film , Thermoplastic , Elastomer, TPE , Polyethylene (PE) , LDPE

Material Notes:

Blending KRATON D and G polymers with PE significantly improves the toughness at both room and low temperatures. KRATON polymers are block segments of styrene and rubber monomers (A-B, A-B-A, or [A-B]n). The KRATON D series consists of an unsaturated polymer, either butadiene or isoprene, as the rubber monomer. Unless otherwise specified, All properties listed below are measured on blown film, 4 mil (100 microns) thick. Information provided by the manufacturer, Kraton® Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kraton-D1102-LDPE-blend-1090.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	9.30 MPa	1350 psi	
Tensile Impact Strength	173 kJ/m²	82.3 ft-lb/in²	
Dart Drop Test	350 g	0.772 lb	Using 2 in. (0.508 cm) dia dart, 60 in. (774 cm) drop height.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China