

Kraton® D1102 + PP blend (50/50)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polypropylene (PP)

Material Notes:

Unmodified polypropylene has high rigidity and good heat resistance, but poor impact resistance, especially at low temperatures. Blending KRATON D and G polymers with PP significantly improves the toughness at both room and low temperatures. KRATON polymers are block segments of styrene and rubber monomers (A-B, A-B-A, or [A-B]_n). The KRATON D series consists of an unsaturated polymer, either butadiene or isoprene, as the rubber monomer. Information provided by the manufacturer, Kraton® Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kraton-D1102-PP-blend-5050.php

Physical Properties	Metric	English	Comments
Melt Flow	1.8 g/10 min	1.8 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	30.0 MPa	4350 psi	
Tensile Strength, Yield	13.5 MPa	1960 psi	
Flexural Modulus	0.600 GPa	87.0 ksi	
Izod Impact, Notched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	3.2 mm (0.125 in) notch
	NB @Temperature 0.000 °C	NB @Temperature 32.0 °F	3.2 mm (0.125 in) notch
Falling Dart Impact	>= 244 J	>= 180 ft-lb	Falling weight impact at 23°C (73.4°F)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China